


MegaFlex



Structure



8-STRAND CONSTRUCTION

Fiber Content

- Polyester & High Tenacity Polypropylene Fiber Mixed

Characteristics

- High strength & Wear resistance
- Lower weight than polyester rope
- Low working elongation
- Superior flexibility
- Non-Torque construction

Applications

- Mooring and Tie-up lines
- Mooring pendants
- Tug assist lines

Dia		Cir	Weight		MBL	
inch	mm		200m/kg	600ft/lb	ton	kN
1-9/16	40	5	182	367	32.00	313.80
1-3/4	44	5-1/2	218	440	38.00	372.70
1-7/8	48	6	260	524	44.00	431.50
2-1/16	52	6-1/2	298	601	52.00	509.90
2-1/4	56	7	355	715	59.00	578.60
2-3/8	60	7-1/2	400	806	67.00	657.00
2-1/2	64	8	447	902	76.00	745.30
2-7/8	72	9	567	1,144	95.00	931.60
3-5/32	80	10	696	1,404	115.00	1,127.80
3-7/16	88	11	836	1,686	140.00	1,372.90
3-13/16	96	12	1,000	2,016	166.00	1,627.90
4-1/8	104	13	1,172	2,362	191.00	1,873.10
4-7/16	112	14	1,345	2,712	219.00	2,147.60
4-3/4	120	15	1,548	3,121	252.00	2,471.30

• ± 5% tolerance according to ISO 2307

